OTC Website

Find Technologies

Permalink

Request Information

Stable Photonic Structures

Tech ID: 32612 / UC Case 2011-315-0

PATENT STATUS

Country	Туре	Number	Dated	Case
United States Of America	Issued Patent	9,734,946	08/15/2017	2011-315

FULL DESCRIPTION

Background

CATEGORIZED AS

Optics and Photonics

OTHER INFORMATION

All Optics and Photonics

- Materials & Chemicals
 - Nanomaterials
- Nanotechnology

Materials

Security and Defense
Other

Sensors & Instrumentation

Analytical

RELATED CASES

2011-315-0, 2007-505-0, 2009-502-0,

2011-245-0

SPM particles with a highly charged electrolyte (e.g., sodium polyacrylate). Over time the photonic properties degrade due to the partial detachment of the polyacrylate molecules from the surface of the SPM particles. **Current Invention**Inventors at UCR have successfully addressed this challenge of partial detachment to ensure the long term stability of the charges on the SPM particle surface. Inventors have developed a patented process for coating the particles with a protective layer of porous silica. By trapping the acrylate polymer chains in its network, the porous silica layer can effectively enhance the charge stability and maintain the long-range electrostatic repulsion, thus producing magnetically tunable photonic structures with consistent performance even after a long period of storage.

Colloidal assembly of photonic materials has become one of the most powerful routes for the fabrication of responsive

suffer charges or other structural factors. Strong electrostatic repulsions can be established by covering the surfaces of

control over the photonic properties by using external magnetic fields. The key to this self-assembly strategy is the establishment of a balance between the magnetically induced dipolar attraction and the repulsions resulting from the

photonic crystals. Inclusion of superparamagnetic (SPM) components into colloidal building blocks allows for effective



Change in (A) peak position and (B) intensity of the diffraction of aqueous solutions containing Fe3O4@p-SiO2 (square) and polyacrylate-capped Fe3O4 particles (circle) assembled under fixed external magnetic fields after the particles are stored in water for various times. For Fe3O4@p-SiO2 particles the field strength is -131G and the field gradient 77.5 G/cm, while for the polyacrylate-capped Fe3O4 particles, the field strength is -162 G and the field gradient is 82.5 G/cm

ADVANTAGES

- ▶ Long term stability of the photonic crystals.
- ▶ Powerful route for the fabrication of photonic crystals.
- ► Consistent performance over time

SUGGESTED USES

- ► Color display devices
- ► Sensors
- ▶ Encryption



tel: .

Venkata S. Krishnamurty venkata.krishnamurty@ucr.edu ► Active optical components

RELATED MATERIALS

▶ Charge Stabilization of Superparamagnetic Colloids for High-Performance Responsive Photonic Structures

University of California, Riverside Office of Technology Commercialization 200 University Office Building, Riverside,CA 92521 otc@ucr.edu https://research.ucr.edu/

Terms of use | Privacy Notice | © 2021 - 2022, The Regents of the University of California